

DOUBLE DUTY DRILL COLLAR & TOOL JOINT COMPOUND

DESCRIPTION

JET-LUBE 21®, an environmentally friendly, doubleduty drill collar and tool joint compound, has been formulated to provide a superior level of performance for the increasing demands of today's oilfield market. The lead-free formulation contains copper flake as the only metallic component and is fortified by a unique blend of natural, inorganic, extreme-pressure, and anti-wear additives. 21 utilizes our EXTREME base grease which is resistant to invert or high-pH muds and provides better pipe storage properties.

- · Not classified as a marine pollutant DOT Approval CA2006100003
- · Contains no lead or zinc.
- · Very good running & storage capability.
- · Formulated with a proprietary blend of copper, graphite, and other additives for protection and prevention of excessive circumferential makeup in hostile drilling environments.
- Inhibitors protect against rust and corrosion.
- Sticks to wet joints.
- · Special complex base for brushability and stability over a wide temperature range.
- · Consistent rig floor makeup.
- Excellent resistance to makeup downhole.
- Available in Arctic, Thermal, and Specialty grades.

JET-LUBE 21 should be utilized with the thread manufacturer's recommended torque by multiplying the torque value by friction factor of1.15. In more severe drilling situations such as higher speeds, higher penetration rates, deviated holes, or harder formations, drill collars and other rotary shouldered connections should be made up an additional 10%. Friction factors for JET-LUBE 21 were developed using full scale API tool Joint connections.

APPLICATIONS

JET-LUBE 21 is recommended for the entire drill string in most drilling conditions. Typical applications would include geothermal wells, high angle holes, and problem holes involving high temperature, whip stocks, and horizontal drilling applications. JET-LUBE 21 prevents high stress in drill pipe connections which shortens their useful life.

PRODUCT CHARACTERISTICS

Thickener Type Color	Complex Petroleum Metallic
Dropping Point (ASTM D-566)	450°F (232°C)
Specific Gravity	1.1
Density (lb. /gal)	9.0
Oil Separation (ASTM D-6184)	<5.0
Wt. % Loss @ 212°F (100°C)	
Flash Point (ASTM D-92)	>430°F (221°C)
NLGI Grade	1
Penetration @ 77°F	310 - 330
(ASTM D-217)	
Copper Strip Corrosion	1A
(ASTM D-4048)	
4-Ball (ASTM D-2596)	
Weld Point, kgf	620
Friction Factor*	1.15
(Relative to API RP 5A3 Annex I)	
Service Rating	0°F (-18°C) to 450°F
	(232°C)

* Many factors such as pipe size, thread geometry, drilling mud contamination, etc. affect the friction factor. This is a relative number and in all applications experience and prior knowledge should be used to adjust make-up torque accordingly.

This thread compound conforms with API RP 5A3 for use with rotary shouldered connections.

Environmental Rating:

UK CEFAS Group B

For package types and part numbers www.jetlube.com/resources/product-index/

Limited Warranty

www.jetlube.com/assets/documents/Jet-Lube Warranty.pdf